



Cold-Seal™

Permanently Tacky Pumpable Seam Sealant

PART NUMBERS

321500 1 5-Gallon Pail

TECHNICAL DATA

Color	Gray
Consistency	Heavy viscous
Base	Synthetic rubber
Solvent	Mineral spirits
Weight per Gallon	9.7 lbs.
Solids Content	86%
Viscosity	Thixotropic
Coverage	1550 linear ft./gal., 1/8 in. bead
Flexibility	Excellent
Time to Test	Immediately
Service Temperature	-30°F to 200°F (-1.1°C to 93.3°FC)
Surface Burning*	Flame spread0 Smoke developed5
Water Resistance	Excellent
Mildew Resistance	Excellent
VOC	198 g/l
Pressure Classes	SMACNA ½, 1, 2, 3, 4, 6 and 10 inches w.g.
Seal Class	Meets Seal Class A
Packaging	5-gal.
Freeze/Thaw Stability	Excellent
*When tested in accordance with A	CTM EQ4

^{*}When tested in accordance with ASTM E84

PRECAUTIONS

COMBUSTIBLE. Harmful if swallowed or inhaled. May cause eye irritation. Keep out of the reach of children. Review Material Safety Data Sheet for complete safety information prior to use

For Industrial Professional Use Only.

Cold-Seal is a cold-applied, non-hardening, fire-retardant seam sealant for use in rectangular, longitudinal, Pittsburgh TM , snaplock or similar metal duct seams. Cold-Seal will not string, saving equipment cleanup labor. In addition, Cold-Seal resists drying in equipment hoses, avoiding costly replacement.

APPLICATION

Temperature	35°F to 90°F (1.7°C to 32°C)
Preparation	Surface must be dry and
	free of dirt, oil and grease.
Rate	Apply $\frac{1}{6}$, bead to seams prior to closing
Clean Up	UN-TACK [™] or Solvent (Use safe handling practices.)

STORAGE

Temperature	35°F to 90°F (1.7°C to 32°C)
Shelf Life	One year (unopened)
Flammability	Combustible. Flash Point 150°F (Tcc). Store according to local codes.



